



TECHNICAL DATA SHEET

LEPAGE®

PLUMBER'S CHOICE Adhesive Sealant

Henkel Canada Corporation

Professional and Consumer Adhesives
Mississauga, ON, L5T 3A5
Phone 1-800-624-7767
Fax (440) 937-7067
www.henkel.com www.lepageproducts.com

DESCRIPTION

LePage® Plumber's Choice Adhesive Sealant is a waterproof, all-purpose adhesive. It forms a watertight seal, dries clear and has a thick, no-drip consistency that won't run. Great for high-moisture plumbing applications and for outdoor waterproof projects and repairs.

RECOMMENDED FOR:

- Sealing leaks, repairing tears, securing tiles, fixing footwear and mending glassware.
- Bonding aluminum, brick, cardboard, ceramic, fabric, fiberglass, glass, leather, most plastics, rubber, steel and wood.

NOT RECOMMENDED FOR:

- Potable water systems
- Polyethylene or polypropylene products

FEATURES & BENEFITS:

Feature	Benefits
All-purpose adhesive.....	Great for everyday projects and repairs
Dries crystal clear.....	Eliminates obvious bond lines achieving invisible repairs
Thick gel-like consistency.....	Will not run or drip; Reduces clean-up
Waterproof.....	Forms a tight, waterproof, weatherproof bond for a superior seal; Great for plumbing repairs
Dries to a semi-flexible bond.....	Ideal for bonding flexible materials such as fabric or leather
Gap filling.....	Will fill and seal uneven surfaces

DIRECTIONS

Tools Typically Required:

Tooling device.

Safety Precautions:

Wear gloves. Use in a well ventilated area.

Preparation:

Protect work area. Surfaces to be glued or sealed must be clean and dry. Pre-fit all materials before applying adhesive. Pierce tube seal with the reverse side of the cap.

Application:

As an adhesive:

Apply adhesive to both surfaces to be bonded. Wait for 5 minutes until adhesive is tacky and then press surfaces together. Clamp if necessary. Sets in approximately 10 minutes and dries in 24 hours. Dry time is dependent upon temperature, humidity and amount of adhesive used.

As a sealant:

Apply a layer ¼" (6 mm) thick bead over the area to be sealed. Tool if desired. Let dry for 24 hours. If necessary apply a second coat.

LePage® Plumber's Choice
Adhesive Sealant



Item #	Package	Size
303383	Carded Tube	59 mL

Clean-up:

Clean tools and uncured product residue immediately with mineral spirits or acetone. Cured product may be carefully cut away with a sharp-edged tool.

STORAGE AND DISPOSAL

NOT DAMAGED BY FREEZING. Store away from heat, flame and spark in a cool, well-ventilated area. Use an approved hazardous waste facility for disposal.

LABEL PRECAUTIONS

FUMES HARMFUL AND MAY CATCH FIRE. Do not swallow. Do not breathe fumes. Do not get in eyes or on skin or clothing. Do not smoke. Use only in a well ventilated area. Keep away from flames, such as a pilot light, and any object that sparks, such as an electric motor. **KEEP OUT OF REACH OF CHILDREN. FIRST AID TREATMENT:** Contains toluene and hexane. If swallowed, call Poison Control Centre or doctor immediately. Do not induce vomiting. If breathed in, move person into fresh air. If in eyes or on skin, rinse well with water.

Refer to the Material Safety Data Sheet (MSDS) for further information

DISCLAIMER

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Purchasers should test the products to determine acceptable quality and suitability for their own intended use. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

TECHNICAL DATA

Typical Uncured Physical Properties		Typical Application Properties	
<u>Colour:</u>	Clear	<u>Application Temperature:</u>	Apply above 32°F (0°C)
<u>Appearance:</u>	Lump-free gel	<u>Odour:</u>	Solvent (use in a well-ventilated area)
<u>Base:</u>	Synthetic rubber	<u>Set Time:</u>	5 minutes
<u>Solvent:</u>	Toluene, hexane	<u>Dry Time:</u>	24 hours (max. strength after 72 hours)
<u>Specific Gravity:</u>	0.90		
<u>Flashpoint:</u> (ASTM D 56 (C22.1))	-5.2 ± 1°C		
<u>VOC Content:</u>	< 48.1% wt (437 g/L)		
<u>Shelf Life:</u>	24 months from date of manufacture (Unopened)		
<u>Lot Code Explanation:</u> (Stamped on crimped end of tube)	For example: LB09AD12 9 = Last digit of the year = 2009 A = Month = January		

Typical Cured Performance Properties

<u>Colour:</u>	Crystal Clear	<u>Water Resistance:</u>	Yes
<u>Cured form:</u>	Non-flammable, semi-flexible solid	<u>Shear Strength:</u> 24 hours, Maple to Maple	465 psi
<u>Service Temperature:</u>	-10°C (14°F) to 43°C (110°F)		