

MATERIAL SAFETY DATA SHEET (MSDS)

All Systems Floor Finish

Gran-Prix XL

Floor Finishes

SECTION I > PROD	DUCT IDENTIFICAT	ION					
Product Name						WHMIS Classification	
					Not Ap	Not Applicable	
SECTION II HAZA	RDOUS INGREDI	INTS					
Chemical Name		Cas Registry No.	%		Toxicity		
Not Applicable				/0		Toxicity	
	ICAL DATA	· · ·					
Appearance	Odour	рН	Boiling Point	Specific G	ravity S	olubility in Water	
White emulsion	Acrylic	8.7	100 °C	1.0		100 %	
SECTION IV FIRE AND EXPLOSION HAZARD DATA							
Flash Point (°C): None Extinguising media: Not Applicable							
Special fire fighting procedures: None							
Unusual fire and explosion							
SECTION V > TOXI	COLOGICAL PROP	EDTIES					
	th = 1 Flammability	= 0 Read	ctivity = 0			Rating System	
Swallowing: Slightly Toxic					0 = Insignificant		
Inhalation: Not Applicable					1 = Slight		
					2 = Moderate		
Skin Contact: Slight Irritant				3 = High			
Eye Contact: Slight Irritant						4 = Extreme	
Special Warning: None							
SECTION VI FIRS	AID MEASURES						
Ingestion: Drink 3-4 glasses	of milk or water.						
Inhalation: Not Applicable							
Skin: Flush with water.							
Eyes: Flush with water. If irritation persists, call a physician.							
SECTION VII	TIVITY DATA						
Stable: Yes							
Conditions to avoid: None							
Incompatibility with other materials: None							
Hazardous decomposition products: None							
Hazardous polymerization							
	ENTIVE MEASURI	ES					
Hand protection: No							
Eye protection: No							
Ventilation: General							
Respiratory protection: No	ne						
Other protective equipmen							
Steps to be taken in case n		l or spille	1: Mop up spillage. Rinse	e spill area with	water and allow	to dry.	
Waste disposal method: Flush with water into waste systems in accordance with municipal, provincial and federal regulations.							
Precautions to be taken in		-	al handling processes. Ir	side storage at	4-40 °C recomm	nended.	
Other precautions: Follow la							
UN: Not Applicable	TDG Clas			king Group: N	ot Applicable		
TDG Emergency Telephone	• Number: 613-996-	6666 (COL	LECT)				
SECTION IX PREF	ERATION DATA						
Prepared by: M. Mikoluk			Last undate	ed: June 1, 201	5		
Location: Dustbane Products Limited, 25 Pickering Place, Ottawa, Ontario, K1G 5P4 – 613-745-6861							
		,	,				

Gran-Prix XL All Systems Floor Finish

"Gran-Prix XL is an innovative floor maintenance solution. With its versatile, acrylic copolymer based formula, it's the perfect floor finish for all maintenance systems."

FEATURES AND BENEFITS

Environmentally Friendly: A.P.E. free

Multi-use: May be used with ultra high speed burnish, dry-bright and spray-buff systems and on all resilient and non-resilient floors except unsealed wood.

Durable: Resists scuffs, scratches, heel marks, etc.

Slip resistant: Produces a safe, slip-free surface.

Easy to remove: Readily removed using conventional strippers.

WHERE TO USE

For use on vinyl, vinyl asbestos, vinyl composition, asphalt, linoleum, rubber, sealed cork, sealed wood, sealed concrete, sealed terrazzo and the so called "no-wax floors".

HOW TO USE

Should be used to protect and enhance the appearance of high profile area floors. May be applied to all resilient and non-resilient floors except for unsealed wood and cork.

Preparation: Before your initial application, the floor must be stripped of any old finish and rinsed thoroughly with potable water and allowed to dry. Sealing the floor is recommended prior to applying a floor finish.

Application: Using a clean mop and bucket, apply 1-3 coats (depending on the porosity of the floor) allowing the floor to completely dry between coats, at least 30 minutes or more.

Maintenance: Sweep or dry mop frequently. Wet mop or auto-scrub periodically with a properly diluted neutral detergent. Scrub and recoat worn traffic areas as required. Spray buff as needed. Remove any surface dirt and dust with a treated mop. Wet mop or auto-scrub periodically with a neutral detergent. Scrub and recoat worn traffic areas as required.

SPECIFICATIONS
Type: Acrylic Copolymer
Appearance: White liquid
Fragrance: Acrylic
Viscosity: As water
Coating Gloss (5 coats): 84 %
pH: 8.7
Non-volatile %: 19.0
Slip Resistance: 0.5 min (ASTM D-2047)
Freeze-Thaw Stability: Passes 3 cycle
Dry Time: 15 minutes
Sugar Refract: 25.7-26.2
WHMIS: No
TDG: No