



Technical Data Sheet

BUTYLOID RUBBER CAULK #1230



Product Description	Butyloid Butyl Rubber Caulk is an elastomer-based sealant exhibiting exceptional adhesion to most common construction surfaces such as metal, glass, wood, brick, stone and paint. It is ideal for sealing narrow openings in mobile homes, skylights and recreational vehicles. Highly recommended to seal the joints in Preserved Wood Foundations (PWF).
Features and Benefits	 Exhibits strong adhesion and flexibility over an broad temperature range. Paint able after 24 hour drying period depending on temperature. Water resistant Up to 15 YEAR LIFE EXPECTANCY LEED Compliance Eligible for credit EQ 4.1 VOC <230g/L
Application	Apply only to clean, dry and sound surfaces. If old caulk is brittle or crumbling, remove it. Use in joints no more than .95cm(3/8") should be built up to within .95cm (3/8") with suitable back-up material.
	RESTRICTIONS: Do not apply when temperature is below 4.4'C(40'F). Care should be taken when using product on plastic as crazing may result. If in question do a small test area first.
	Trim nozzle to desired bead size, puncture membrane at inner base of nozzle, and apply with standard caulking gun. Clean tools with mineral spirits.
Coverage	25 Linear feet per 300ml @ .64cm(1/4") X .64cm(1/4")
Cautions	 Combustible! Keep away from heat and open flame. Do not take internally. KEEP OUT OF THE REACH OF CHILDREN

To find out more about our line of GH International products, contact us at: T 905-677-5522 F 905-677-5336 or visit our website at www.ghinternational.com

Physical Properties

Percent Solids	
Through dry Time	7-14 Days
Paint ability	
Weatherability	Good
Water Impermeability	
Service Temperature Range	-34 °C to +82°C(-30° to 180°F)
Flash Point.	40°C(100'F)

Limited Warranty

If this product is proven to have a manufacturing defect, we will provide you with replacement value or product, at our option, for the defective product. This commitment is our full representation regarding the product and is in lieu of all expressed or implied warranties and may not be extended by representatives, written sales information, drawings or otherwise. IN NO EVENT SHALL THE MANUFACTURER OR ITS AFFILIATES BE LIABLE FOR ANY INDIRECT, ASSOCIATED, INCIDENTAL OR CONSEQUENTIAL DAMAGES.