



# TECHNICAL DATA SHEET



**Henkel Canada Corporation**  
Professional and Consumer Adhesives  
Mississauga, ON L5N 6C3  
Phone 1-800-624-7767  
Fax (440) 250-9661  
[www.henkel.com](http://www.henkel.com) [www.lepage.com](http://www.lepage.com)



## DESCRIPTION

LePage® No More Drafts™ Removable Weather Stripping is a temporary indoor and outdoor sealant, which effectively aids in preventing cold air and drafts from entering. Its unique properties enable it to be applied in the Fall and peeled off effortlessly in the Spring. No More Drafts™ Removable Weather Stripping fills hard-to-seal gaps better than tape and dries to a transparent bead providing an invisible seal. It will not harm painted or stained surfaces and can be painted over.

## RECOMMENDED FOR:

Seals around windows, doors, air conditioners, baseboards and wall outlets. Bonds to wood, metal, glass and masonry surfaces.

## NOT RECOMMENDED FOR:

- Contact with oil-based caulking, silicone sealant, polysulfide or fillers impregnated with oil
- Continuous water submersion applications
- Freshly treated wood. It must have been weathered for at least 6 months.

## FEATURES & BENEFITS:

Feature	Benefits
Transparent.....	Invisible seal
Water resistant.....	Indoor or outdoor use
Paintable.....	Blends with surroundings
Prevents cold air and drafts from entering.....	Energy cost saving
Temporary sealant.....	Ease of removal

## COVERAGE

A 1/4" (6 mm) bead extrudes approximately 9.3 m (31 ft.).  
A 3/8" (9.5 mm) bead extrudes approximately 4.2 m (14 ft.).

Item #	Package	Size
1732921	Paper Cartridge	295 mL

## DIRECTIONS

### Tools Typically Required:

Utility knife, caulking gun, long and thin tool to puncture cartridge seal, tooling device.

### Safety Precautions:

Apply in a well ventilated area. Wear gloves and wash hands after use.

### Preparation:

Use above 5°C (41°F). Surfaces must be clean, dry and free of grease, frost, dust and other contaminants. Complete preparatory work before opening sealant. Cut nozzle at a 45° angle to desired bead size and puncture inner seal.

**Application:**

Apply sealant with a steady pressure, forcing into the joint. For easier removal, leave the sealant in rounded beads. Do not use in joints deeper than 12 mm (1/2") without the use of a backer rod. Use in joints between 6 mm (1/4") and 19 mm (3/4") wide. The strong odour will dissipate within 24 hours. For removal, undercut the sealant with a sharp knife and gently pull it away from the surface towards you.

**Clean-up**

Clean tools and sealant residue immediately with mineral spirits. Sealant can be easily removed after the season. To remove, cut with a knife below the sealant and pull away from the surface towards you.

**STORAGE AND DISPOSAL**

Not damaged by freezing. Use an approved hazardous waste facility for disposal.

**LABEL PRECAUTIONS**

**DANGER. FLAMMABLE. POISON. FUMES MAY CATCH FIRE. CONTENTS MAY BE HARMFUL.** Do not breathe fumes. Use only in a well ventilated area. Wear a mask. Do not smoke. Keep away from flames, sparks and any other object that sparks, such as a pilot light or electrical motor. **KEEP OUT OF REACH OF CHILDREN.**  
**FIRST AID TREATMENT:** Contains naphtha. If breathed in, move person into fresh air.

**Refer to the Material Safety Data Sheet (MSDS) for further information**

**DISCLAIMER**

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Purchasers should test the products to determine acceptable quality and suitability for their own intended use. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

**TECHNICAL DATA**

Typical Uncured Physical Properties		Typical Application Properties	
<u>Colour:</u>	Clear	<u>Application Temperature:</u>	Do not apply below 5°C (41°F)
<u>Appearance:</u>	Non-slumping paste	<u>Tack-free time:</u>	30 minutes @ 25°C (78°F)
<u>Base:</u>	Synthetic rubber	<u>Dry time:</u>	24 hours @ 25°C (78°F) and 50% RH
<u>Solvent:</u>	Hydrocarbon blend	<u>Odour:</u>	Solvent (use in a well-ventilated area)
<u>Viscosity:</u>	650 Mcps @ 5 rpm	<u>Sag:</u>	7.5 mm maximum
<u>Specific Gravity:</u>	0.86		
<u>Flashpoint:</u>	25°C (77°F)		
<u>% Solids:</u>	42.8 %		
<u>VOC Content:</u>	56% by weight (< 485 g/L)		
<u>Shelf Life:</u>	24 months from date of manufacture (unopened)		
<u>Lot Code Explanation:</u>	YYDDD YY = Year of manufacture DDD = Day of manufacture based on 365 days in a year		
(Lot code stamped on bottom of cartridge plunger)	For example: 13061 = 61 <sup>st</sup> day of 2013 = March 2, 2013		

<b>Typical Cured Performance Properties</b>
---

<u>Colour:</u>	Clear	<u>Water Resistance:</u>	Yes
<u>Cured form:</u>	Non-flammable, elastomeric solid	<u>Sandable:</u>	No
<u>Service Temperature:</u>	-30°C (-22°F) to 38°C (100°F)	<u>Paintable:</u>	Yes, after 7 days.